

MEASUREMENT PROTOCOL


No. PM_IRT_OPT_23_06_30_01

PO number / date order from 30.5.2023
Customer ALPHA CZECH s.r.o.
Sample ID customer THRcoating ALPHA, thickness 0.55 mm
 NTC 230607-002/001
Quantity SRI
Measurement method SNHRRT - UV-VIS-NIR, SNHRRT/V1 - MIR
Standard ASTM E1980-11
Date 15.6.2023
Measured by Martina Veselá, DiS.
Responsible person Ing. Petra Honnerová, Ph.D. tel.: +420 735 713 911
 e-mail: petrahon@ntc.zcu.cz

Thermal emissivity (-)	0.866	Standard	ASTM E408-13
Solar reflectance (%)	81.7	Standard	ASTM E903-12

	low	high	medium
Convective coefficient (W/m ² ·K)	5	12	30
Surface temperature (°C)	48.2	43.9	40.4
SRI (-)	101.9	101.9	101.9

conditions (see ASTM E1980-11 Standard)
 standard solar radiation conditions
 solar flux = 1000 W/m²
 ambient air temperature = 37°C
 sky temperature = 27°C
 conduction heat transfer is not included



Západočeská univerzita v Plzni
 Nové technologie - výzkumné centrum
 Infračervené technologie