

CLASSIFICATION REPORT FOR ROOFS EXPOSED TO EXTERNAL FIRE

Subject of
classification:

*Roofs and roof coverings
in accordance with EN 13501-5:2017, cl. 8.4 and 9*

Report No.:

PK5-03-25-009-E-0

Product name:

*Roof with ALPHA FLEXIBLE waterproofing and reflective
insulation coating*

Sponsor

ALPHA CZECH s.r.o.
U Plynárny 348/83
101 00 Prague – Michle
Czech Republic

Prepared by:

PAVUS, a.s.
Certification body for product certification No. 3041
– accreditation issued by Czech Accreditation Institute, p. s. c.,
– Certificate of Accreditation No. 16/2024

Prosecká 412/74
190 00 PRAGUE 9
Czech Republic

Order No. Z210250204

Date of issue:

2025-10-15

Copies in total:

2

Copy number:

1

Pages in total:

3



1 INTRODUCTION

- 1.1 This classification report defines the classification assigned to roof with *ALPHA FLEXIBLE waterproofing and reflective insulation coating* in accordance with the procedures given in EN 13501-5:2016.
- 1.2 This classification report consists of 3 pages and may only be used or reproduced in its entirety.

2 DESCRIPTION OF THE ROOF

The roof with *ALPHA FLEXIBLE waterproofing and reflective insulation coating* comprises:

- **ALPHA FLEXIBLE**, waterproofing and reflective insulation coating, coating thickness 400 microns
- **Paraelast ANTIFIRE G S50**, thickness 5,2 mm
- **Sklodek 40 SPECIAL MINERAL** thickness 4 mm
- **Standard chipboard base**, thickness 16 mm, bulk density 680 kg/m³

The top coat is applied directly to Paraelast, which is then screwed to the base plate.

3 REPORTS AND RESULTS IN SUPPORT OF THIS CLASSIFICATION

3.1 Reports

Name of laboratory Address Accreditation number	Name of sponsor	Report ref. No. Date of issue	Test method and date / field of application rules and date
PAVUS, a.s. Veselí nad Lužnicí ATL No. 1026	ALPHA CZECH s.r.o. U Plynárny 348/83 101 00 Prague – Michle Czech Republic	Pr-25-2.154-En 2025-10-06	ČSN P CEN/TS 1187:2012 – Test 3

3.2 Test results

Test conditions:

Test pitch: 5°

Supporting deck: wood particle board deck with gaps of (5.0 ± 0.5) mm between planks



Parameter	Criteria			Test results		Compliance		
	Class B _{ROOF} (t3)	Class C _{ROOF} (t3)	Class D _{ROOF} (t3)	Specimen 1	Specimen 2	Class B _{ROOF} (t3)	Class C _{ROOF} (t3)	Class D _{ROOF} (t3)
External fire spread time T_E	$\geq 30 \text{ min}$	$\geq 10 \text{ min}$		30 min	30 min	yes	-	-
Time to fire penetration T_P	$\geq 30 \text{ min}$	$\geq 15 \text{ min}$	$> 5 \text{ min}$	-	-	yes	-	-

4 CLASSIFICATION AND FIELD OF APPLICATION

4.1 Reference

This classification has been carried out in accordance with EN 13501-5.

4.2 Classification

The roof with *ALPHA FLEXIBLE waterproofing and reflective insulation coating* in relation to its external fire performance is classified:

B_{ROOF}(t3)

4.3 Field of application

This classification is valid for the following conditions:

Range of pitches: $< 10^\circ$

Range of decks:

- any wooden continuous deck with a minimum thickness of 12 mm;
- any deck made from wooden planks with plain edges;
- any non-combustible deck with gaps not exceeding 5 mm.


5 LIMITATION

This classification is valid unless the conditions, under which it was issued, have been changed (i.e., until the materials used, the composition or design of the product or the technical regulations relating to the product change).

The sponsor may request the issuing authority to review the influence of changes on the classification validity.

This classification document does not represent type approval or certification of the product.


Elaborated by:


 Roman DEDEK
 Fire Testing Laboratory

Reviewed by:


 Jaroslav KOPEČNÝ

Approved by:


 Jan TRIPES, MBA

PAVUS, a.s.
 Čtvrť J. Hybeše 879
 391 81 Veselí nad Lužnicí
 IČ: 60193174; DIČ: CZ60193174
 (8)

