

Technical and material data sheet

ABAMAL DEEP PENETRATION



Reflexně izolační
nátěry

Downloads



5L



2L

Číslo šarže: etiketa

Datum výroby: etiketa

Datum expirace: 12 / 24 měsíců / etiketa

Poslední revize: 15.11.2023

Verze: 02 Pouze pro domácí použití

The product ABAMAL Deep Penetration is a deep penetrating coating. It acts as an adhesion bridge and primer to strengthen and reduce the absorbency of the surface material. The product is vapour permeable. Use on all mineral and concrete surfaces. The coating is health friendly and environmentally friendly.

Main properties

- Penetrating interior coating
- Unification of different absorbency of the surface
- Strengthening of the surface
- Increase the adhesion of other coatings

Application

ABAMAL Deep Primer is used as a penetrating and adhesion coating for ABAMAL interior coatings.

Technical properties

Theoretical consumption ¹	100 ml/m ²
Practical consumption	Practical consumption depends on many factors such as porosity, surface roughness and material loss during application.
Dilution	Not diluted
Recommended wet film layer	100 µm
Stirring	Always the whole package before opening
Stirring during prolonged application	Stir every 40 minutes
Packaging	2 and 5 litres / 2 and 5 kg
Density	1,01 g/cm ³
Appearance	White
Colour	Cannot be coloured
Gloss level	Matte

Odour	Odourless
Shelf life ²	24 months, must not freeze
Flash point	Non-flammable

Repaintability and curing time ³

To the touch	1 hour
For handling	1 hour
For the next layer	2 hours
Fully dried	24 hours

Safety instructions **Read the Technical and Safety Data Sheet**

1 Consumption depends on the surface

2 Stored in original and sealed containers at a temperature between +5 °C - +35 °C

3 At +20 °C and 50% PH

Surface preparation

The surface must be free of loose elements, dry, firm, free of oil and grease stains, free of dust, mould, salts, rust and old incoherent coatings. The surface must be perfectly hardened and structurally uniform. Before applying the technology, the surface must be perfectly mature. We first apply to fresh plaster after it has dried completely.

Suitable for all porous surfaces such as concrete, raw masonry surfaces, stone, unglazed ceramics, plaster, plasterboard, etc,

Procedure and application / tools

The penetrant must be thoroughly mixed before use! Always mix the entire contents of the package!

On properly prepared surfaces, ABAMAL Depth Primer can be applied in one, ideally up to two layers depending on the surface properties, preferably with a soft brush or roller, in a crosswise manner.

The material consumption is influenced by the surface texture and the method of application. Apply the primer in single layers as required. The primer must be mixed during prolonged application. In case of higher ambient temperatures (e.g. direct sunlight), mix the coating more frequently. The primer should not be handled in damp environments.

After approx. 2 hours, once the surface is dry to the touch, continue with a second layer. Avoid applying excessive amounts and prevent puddles from forming. Apply the penetrating coating in complete areas.

Do not apply coating if

- the coating must not be exposed to direct rain for at least 6 hours after application
- the relative humidity is higher than 80%
- the surface moisture content is greater than 4% by weight (concrete: > 2.5%)
- the temperature of the surface (surface) and the environment is below +17 °C
- the ambient temperature is above +35 °C
- the surface is exposed to direct sunlight and the ambient temperature is above +35 °C

After opening the original packaging, it is recommended to consume the contents as soon as possible, keep unused primer in a sealed container with as little air above the surface as possible. The applied primer must not be exposed to direct steam, water or other liquids for long periods of time.

Cover areas where primer will not be applied with material to protect unpainted surfaces from contamination: masking film, non-woven fabrics, tape, etc.

Application conditions

- Surface temperature: +17 °C min. +30 °C max.
- Ambient temperature: +17 °C min. +30 °C max.
- Relative humidity: < 80 %

Drying conditions

Penetration does not require any special measures during drying (curing). Drying time depends on air temperature, humidity and surface temperature. The average drying time per layer is a maximum of 2-4 hours.

Drying time

Drying time depends on the surface temperature and humidity. The maximum drying (curing) time is 24 hours. Apply the next layer only after the previous layer has completely dried. The ambient temperature during drying must be at least +17 °C, ideally +23 °C.

Cleaning tools

With water - as soon as possible after use.

Storage / transport / shelf life

This product retains its useful properties for at least 24 months from the date of manufacture when stored in the prescribed manner in the sealed, intact original packaging. Store at a temperature of +5 °C to +35 °C, humidity up to 80 %. The temperature during transport of the material should not fall below +5 °C and rise above +35 °C. Protect the product from direct sunlight, frost and high temperatures during transport and storage.

Notice

The products can be applied when the surface temperature is above +17 °C and the air temperature is between +23 °C and +30 °C. Avoid application if adverse weather conditions are expected during the curing period (wind, increased dustiness, rain, frost).

Read the Technical and Material Data Sheet, Safety Data Sheet and Application Manual before use.

Note

The information contained in the Technical Data Sheet corresponds to our current knowledge of the manufacturer. Products are of the highest quality and uniform within manufacturing tolerances. The values and data given in this Technical Data Sheet are based on the results of laboratory tests and manufacturer's testing.

The information given, especially the advice for the processing and use of the coating, is based on experience with practical applications under standard conditions and proper storage and use.

These values may vary with practical application. Due to variations in processing conditions and other external influences, and the different nature and treatment of surfaces, a procedure based on the information given, or other written or oral recommendations, may not always guarantee a satisfactory working result. All recommendations made by the manufacturer or distributor of the coating are general. The applicator must verify that the coatings are suitable for the intended purpose of application. The latest edition of the application instructions and product data sheet should always be followed. These, together with other information, are available on request from the manufacturer. Purchasers and users are encouraged to perform a self-test on a sample of the area to be coated prior to application.

The manufacturer shall not be liable for defects resulting from failure to follow the instructions for use given in the Technical and Material Data Sheet, Safety Data Sheet and Application Manual.

Precautions for handling the products

The coating does not contain substances harmful to health, is not labelled or classified as hazardous to health.

Safety precautions

Use protective equipment such as goggles, gloves, protective clothing, etc. to protect eyes and skin. Protect the respiratory tract with a suitable respirator in confined spaces and during spray application. Provide ventilation in case of application in enclosed rooms. More detailed information on hygiene, occupational safety and environmental protection is given in the safety data sheet.

Wash splashed skin with soap and water. Rinse mouth with water if swallowed. If eyes are affected, flush with a stream of water. Exit to fresh air if inhaled.

The material is non-flammable. In the event of a fire in structures, equipment or buildings to which the coating has been applied, we recommend the use of water, foam, dry chemical extinguishing agents or carbon dioxide to extinguish the fire. In the event of a coating leak or spill, use any absorbent material such as sand, etc.

Disposal of packaging/product

The material is not classified as an environmentally hazardous substance (Act No. 185 2001 Coll. on Waste). Dispose of unused material or packaging in accordance with applicable regulations. Clean packaging: category 'O' 15 01 02 - Plastic packaging; Product residues: category 'O' 08 02 99. Keep out of reach of children. Packaging is fully recyclable.

Date of last revision

1.2.2023

Version

For professional use only

Producer



ALPHA CZECH s.r.o.

Na Příkopě 854/14

110 00 Praha 1 – Nové Město

Czechia

www.alphaczech.com